SWEET ’N DILL DESIGNS

DTF Application Instructions

For best results, please follow our recommended pressing instructions.

TEMPERATURE

300°F

Preheat your heat press.

PRESSURE

Medium

Even, medium pressure.

INITIAL PRESS

18 seconds

Press the transfer in place.

PEEL

Wait ~30 sec

Our transfers are hot or cold peel; however, we recommend waiting approximately 30 seconds before removing the film.

FINAL PRESS

18 seconds

Cover your design with a Teflon sheet and press for an additional 18 seconds.

Need a Teflon sheet? Just let us know! We’re happy to provide one complimentary, reusable Teflon sheet per customer to help you achieve the best results with your transfers.

Please keep in mind that heat press temperatures and pressure settings may vary by machine. Thank you for supporting Sweet ’N Dill Designs. Happy pressing!

Sweet ’N Dill Designs
Custom DTF transfers & apparel • Panama City, FL
sweetndilldesigns.com
sweetndilldesigns@icloud.com